

TECHNICAL DATA SHEET

Lettura 80 OFFICE – 80 g / m²

Property	Norm	Unit		
			Target value	
Substances, Grammage	ISO 536	g/m ²	80	
Mositure, relativ	ISO 287	%	30	
Thickness	ISO 534	µm	103	
Opacity	ISO 2471	%	95	
Brightness R457 (D65/10°)	ISO 2470-2	%	80	
Whiteness CIE	ISO 11475	%	88	
Water absorption Cobb	DIN EN 20535	g/m ²	25	
Breaking length, längs	DIN EN ISO 1924	m	4500	
Roughness	ISO 8791-2	ml/min	250	
Bending stiffness	DIN 53121	Nmm	0,13	
pH - value	DIN 53124		7,0	
Surface resistance	DIN IEC 60093	Ohm		
Surface strength	ISO 3783	m/s	2	
Abrasion resistance	DIN 53109	mg		
Toner adhesion	DIN EN 12283		> 0,8	
Cut quality	DIN 12281	Anhang C	95% < 5 98% < 6	