

GREEN LABEL



100 %
Recycled



80
ISO



80
gsm

Saveco Green Label office paper is made from 100% recycled fibre in an integrated, energy-efficient and resource-friendly process that is entirely chlorine free. This high-performance multi-purpose paper has excellent eco credentials, including Blue Angel and FSC Recycled® certification. Ideal for all types of corporate communications, it comes in a wide range of sizes and weights. It also offers excellent runnability and processing as per **DIN EN 12281**.



Technical data

Grammage	ISO 536		gsm	80 ± 3,2
Caliper	ISO 534		µm	101 ± 6,0
ISO brightness	ISO 2470	ISO Brightness	%	80 ± 2,5
CIE whiteness	ISO 11475	CIE Whiteness	%	85 ± 2,5
Opacity	ISO 2471	Duplex	%	≥ 95
Bendtsen roughness	ISO 8791-2		ml/min.	320 ± 160

Certification



www.blauer-engel.de/uz14



Das Zeichen für verantwortungsvolle Walddwirtschaft



Runnability/ resistance to ageing



DIN 6738 (LDK 24-85)

Product complies with DIN EN 12281; resistant to ageing as per DIN 6738 (lifespan class 24-85).



Product description

Raw material
Filler
Surface
Sizing
Auxiliary material

Multifunctional office paper for laser and inkjet printers

wood pulp-containing and wood-free press waste paper from printing companies and collections, according to the regulations of the Blue Angel (RAL-UZ 14)
kaolin and calcium carbonate
starch treated
neutral sizing with synthetic sizing agents
the auxiliary material used are free from organic chlorine compounds and do not lead to the formation of AOX

Application areas

photocopiers, side printer (LED, laser, magnet, ions),
inkjet printer, fax, pre-printing

Assortment

80, 90, 100 and 120 g/gsm
A4, A3, SR A3 and reels,
as well as punched, double and 4 times punched
Further products on request

Manufacturer

Schönfelder Papierfabrik GmbH
Tannenberger Straße 4
09456 Annaberg-Buchholz – Germany



Certifications of the manufacturer



Storage conditions

optimal room temperature min. 10 °C max. 30 °C
Relative humidity min. 30% RH max. 70% RH
Close opened package again when not in use

Processing recommendation

Allow the paper to adapt to the room climate 24 hours before use.
Best runability between 18 °C and 24 °C temperature and between 40% RH and 60% RH relative humidity

Recycling

This product can be 100% recycled after use.