



Ô[[[Â[] ^ Á Á&ææ] [^••â } æ^ Á&ææ æ& Á&æ] ^,
 åæ& [[[á:â] æ æ& Á ææ [æ^& } Á&ææ] æ&æ ææ^ Á&æ [[[áæ^:È
 / Á^!^ææ ^} c^ Á&æææ^! Á^! Á[& { ^} æ^ æ&æ!^•^} ææ } È
 { æ^ æ&æ ææ ææ } åæ&æ ææææ ææææ ææ^ Á^ • c^ È:æ&ææ^ ^ dæ^ Á&æ

Dati Tecnici

COLOR COPY

Grammage	m ²	ISO 536
Caliper	mm/1000	ISO 534
Stiffness L&W	mm/m	mN ISO 2493
Stiffness L&W		ISO 2493
Smoothness Bekk	sec	ISO 5627
Opacity	%	ISO 2471
Brightness with UV	D65 %	ISO 2470
CIE Whiteness		ISO 11475

100	160
100 ± 4.0	160 ± 6.0
106 ± 4	166 ± 6
160 ± 30	490 ± 40
90 ± 25	250 ± 30
105 ± 25	105 ± 25
min 93.0	min 97.0
110.0 ± 1.5	110.0 ± 1.5
161 ± 3.0	161 ± 3.0

Product meets EN 12281, requirements for copy paper for dry toner imaging processes and ISO 9706, requirements for permanence for paper.
 Production processes certified according to ISO 9001, 14001 and 18001.

SIGNIFICANCE OF VALUES: 2 SIGMA





Color Copy - the leading paper guarantees you needle-sharp printouts and brilliant colour reproduction, especially with digital colour laser printing. It is perfectly suitable for documents such as presentations, direct mailings, manuals, corporate plans, business cards and envelopes. Now CO2 neutral!

Technical Data: COLOR COPY

				200
Grammage	g/m ²	ISO 536		200 ± 6.0
Caliper	mm/1000	ISO 534		200 ± 7
Stiffness L&W	MD mN	ISO 2493		min 620
Stiffness L&W	CD mN	ISO 2493		min 330
Smoothness Bekk	sec	ISO 5627		160 ± 40
Opacity	%	ISO 2471		min 98.0
Brightness with UV	D65 %	ISO 2470		110.0 ± 1.5
CIE Whiteness		ISO 11475		161 ± 3.0

Product meets EN 12281, requirements for copy paper for dry toner imaging processes and ISO 9706, requirements for permanence for paper.
Production processes certified according to ISO 9001, 14001 and 18001.

SIGNIFICANCE OF VALUES: 2 SIGMA

