



## SPECIFICATION SHEET




Unit  
Amritsar

Product: Copier

SUBSTANCE (GSM) TAPPI T 410 om-98	CALIPER ( $\mu\text{m}$ ) TAPPI T 411 om-97
80	104
TOL: $\pm 2.5\%$	$\pm 5\%$

PARAMETER	UNITS	VALUE
BREAKING LENGTH MD CD TAPPI T 404 cm-92	Meters	5500 MIN 2500 MIN
TEAR FACTOR TAPPI T 414 om-98	CD	55 MIN
Brightness TS TAPPI T 452 om-98	%	82 MIN
Opacity TAPPI T 519 om-96	%	93 MIN
Roughness (Bendtsen) TS WS ISO 8791-2	ML/Min	240 MAX 320 MAX
Wax Pick TS TAPPI T 459 om-93	NO	16A MIN
COBB 1 MIN TS WS TAPPI T 441 om-98	GSM	26 MAX 27 MAX
Moisture TAPPI T om-94	%	4.0 - 5.0

### CONSTRUCTION



### Note :

1. All Properties Testing Climate 50% RH & 23°C (as per, TAPPI T 402 sp-98).
2. All properties are according to Khanna Paper Mill Ltd. Unit-Amritsar Measurements.
3. Tolerances are based upon 2 sigma level of random samples.